

FLH3 FLOOR HARDNER **DESCRIPTION**

METALLIC FLOOR HARDENER is a mixture of finely graded non-metallic emery aggregates, plasticizer and cement binder. It is an economical concrete floor hardener recommended for both interior and exterior use. When applied at the proper point in the concrete setting cycle, METALLIC FLOOR HARDENER is worked into the concrete to become an integral part of the floor to provide a surface which is highly resistance to abrasion .METALLIC FLOOR HARDENER is available in a natural concrete color in addition to a variety of other colors, including Light Reflective, Tile Red, French Gray and Nile Green.

FEATURES/BENEFITSFEATURES

- Increases impact and abrasion resistance up to four times that of plain concrete
- Provides a high density surface that resists liquid penetration and is easy to clean and maintain
- Minimal surface dusting
- Exterior/interior application
- Non-fading, non-rusting colors (Light Reflective, Tile Red, French Gray and Nile Green)

APPLICATION

Coverage: 0.5 to 1.5 lbs per sq. ft.

(Recommended minimum application rate for colored hardeners is 1.5 lb per sq-ft)

As a general guide to floor and slab construction, refer to American Concrete Institute Standard 302.

All work should be done under roof if at all possible. Job conditions that affect drying/setting time also affect the hardener application time. Use experienced workers for the job size. For most applications, a mechanical spreader that drops the dry shake directly onto the fresh concrete is recommended.

Preparation: Calculate the number of bags required for a given area as per the coverage rate required. Place concrete to finish grade level and compact with a wooden bull float.

Special Conditions: When slab is subjected to any condition that causes rapid surface drying such as low humidity, wind, sunlight, etc., spray MKP Film onto surface just after bull floating.

APPLICATION

Placing: Application of the hardener depends on the following: slump of concrete, job site conditions affecting drying, and the coverage of the hardener. Perimeter sets quicker than interior. Be aware of this and apply to the edges first.

Dry-shake surface hardeners are designed to be placed after bleeding. After concrete has been screed, tamped and floated, apply 2/3 of coverage ratio on first application. Allow the dry-shake to darken, absorbing the moisture from the slab, then wood bull float or machine at the appropriate time. Immediately follow with the remaining 1/3 and machine float. Final finish after the slab stiffens.

To achieve maximum appearance and performance, float and finish the dry-shake so as to maintain the material on the top surface of the slab, fully integrated into the base concrete.

Edges should be worked by hand, keeping trowel as flat as possible. Blistering can occur when trowel blades have been raised too early. Re-trowel with blades lowered to remove blisters

Curing: Apply an approved MKP CHEMICALS ASTM C-309 compliant curing compound after final troweling

PACKAGING

25 Kg lined bag

SHELF LIFE

Shelf life of unopened bags stored in a dry facility is 12 months. Excessive temperature differential and/or high humidity can shorten the shelf life expectancy. Store in a cool, dry area away from direct sunlight

LIMITATIONS/PRECAUTIONS

- DO NOT place at temperatures below 40_F(5_C) or if the temperature is expected to fall below 40_F(5_C) in the next 24 hour period.
- DO NOT use dry-shake hardeners where floor will be exposed to any material known to attack Portland Cement such as acid.
- Slump should not exceed 4+(10.16 cm)
- DO NOT use any air entrainment. Total air in concrete mix should not exceed 3%.
- DO NOT use calcium chloride or aggregates contaminated by salt water.

Caution. Contains Portland Cement and sand. Cement will cause irritation. Avoid contact. Use of dust respirator, safety goggles and rubber gloves is recommended. Avoid prolonged contact with clothing. In case of contact with eyes, immediately flush with water for at least 15 minutes. Get prompt medical attention. DO NOT wear contact lenses when working with this product. DO NOT take internally. Keep out of reach of children

Avoid hazards by following all precautions found in the Material Safety Data Sheet (MSDS), product labels and technical literature. Please read this information prior to using the product.

WARRANTY

NOTICE-READ CAREFULLY CONDITIONS OF SALE

MKP CHEMICALS offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of MKP CHEMICALS. No other representative of or for MKP CHEMICALS is authorized to grant any warranty or to waive limitation of liability set forth below.

WARRANTY LIMITATION

MKP CHEMICALS warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, MKP CHEMICALS will replace the defective product with new product without charge to the purchaser. MKP CHEMICALS makes no other warranty, either ex-pressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

INHERENT RISK

Purchaser assumes all risk associated with the use or application of the product.

